

PCTWORLD INTELLECTUAL PROPERTY ORGANIZATION
International Bureau

INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

(51) International Patent Classification ⁶ : C09J 167/04, C08G 63/08, C08L 67/04	A1	(11) International Publication Number: WO 95/10577 (43) International Publication Date: 20 April 1995 (20.04.95)
(21) International Application Number: PCT/US94/09666 (22) International Filing Date: 25 August 1994 (25.08.94) (30) Priority Data: 08/136.670 15 October 1993 (15.10.93) US (71) Applicant: H.B. FULLER LICENSING & FINANCING INC. [US/US]; 1100 North Market Street, Wilmington, DE 19890 (US). (72) Inventors: EDGINGTON, Garry, J.; 3656 Auger Lane, White Bear Lake, MN 55110 (US). RYAN, Christopher, M.; 16251 125th Avenue, Dayton, MN 55327 (US). (74) Agent: DAIGNAULT, Ronald, A.; Merchant, Gould, Smith, Edell, Welter & Schmidt, 1000 Norwest Center, 55 East Fifth Street, St. Paul, MN 55101 (US).		(81) Designated States: AU, CA, JP, KR, European patent (AT, BE, CH, DE, DK, ES, FR, GB, GR, IE, IT, LU, MC, NL, PT, SE). Published <i>With international search report.</i>
(54) Title: BIODEGRADABLE/COMPOSTABLE HOT MELT ADHESIVES COMPRISING POLYESTER OF LACTIC ACID (57) Abstract A hot melt adhesive composition can be made using a polyester derived from 2-propanoic acid (lactic acid). A thermoplastic resin grade polyester can be formulated into a functional adhesive using adhesive components. A lower molecular weight material can be used as a tackifying resin with a biodegradable/compostable resin in a formulated hot melt adhesive. The adhesive material can be made pressure sensitive and can be made entirely biodegradable by combining the polyester polymer with other biodegradable/compostable ingredients. The resulting adhesive composition can be used in a variety of applications. The biodegradable/compostable adhesive material can be used as a substitute for non-biodegradable materials made from commercial polymers that resist attack by bacteria, fungi and other microbial populations. The hot melt adhesives can be used in (e.g.) packaging and the manufacture of disposable articles which are made from degradable materials. The entire disposable article can be made from adhesives and structural materials that are fully biodegradable/compostable.		

FOR THE PURPOSES OF INFORMATION ONLY

Codes used to identify States party to the PCT on the front pages of pamphlets publishing international applications under the PCT.

AT	Austria	GB	United Kingdom	MR	Mauritania
AU	Australia	GE	Georgia	MW	Malawi
BB	Barbados	GN	Guinea	NE	Niger
BE	Belgium	GR	Greece	NL	Netherlands
BF	Burkina Faso	HU	Hungary	NO	Norway
BG	Bulgaria	IE	Ireland	NZ	New Zealand
BJ	Benin	IT	Italy	PL	Poland
BR	Brazil	JP	Japan	PT	Portugal
BY	Belarus	KE	Kenya	RO	Romania
CA	Canada	KG	Kyrgyzstan	RU	Russian Federation
CF	Central African Republic	KP	Democratic People's Republic of Korea	SD	Sudan
CG	Congo	KR	Republic of Korea	SE	Sweden
CH	Switzerland	KZ	Kazakhstan	SI	Slovenia
CI	Côte d'Ivoire	LI	Liechtenstein	SK	Slovakia
CM	Cameroon	LK	Sri Lanka	SN	Senegal
CN	China	LU	Luxembourg	TD	Chad
CS	Czechoslovakia	LV	Latvia	TG	Togo
CZ	Czech Republic	MC	Monaco	TJ	Tajikistan
DE	Germany	MD	Republic of Moldova	TT	Trinidad and Tobago
DK	Denmark	MG	Madagascar	UA	Ukraine
ES	Spain	ML	Mali	US	United States of America
FI	Finland	MN	Mongolia	UZ	Uzbekistan
FR	France			VN	Viet Nam
GA	Gabon				

BIODEGRADABLE/COMPOSTABLE HOT MELT ADHESIVES
COMPRISING POLYESTER OF LACTIC ACID

Field of the Invention

5 The invention relates to biodegradable/compostable
adhesive compositions that are useful in a variety of
applications. The adhesives can take virtually any form, but
preferably are used as hot melt adhesives. Such adhesives
can be used in applications including case and carton
10 sealing, book binding, bottle labeling, film laminating, etc.
More particularly, the adhesives can be formulated to produce
hot melt pressure sensitive properties and can be applied in
the construction of disposable articles including infant
diapers, incontinent pads and sanitary applications.

15

Background of the Invention

Adhesive compositions are commonly manufactured by
combining thermoplastic resins or similar polymeric materials
with available plasticizers, tackifiers and other additives
20 to produce a wide range of adhesive properties. Common
tackifiers or plasticizers are petroleum based or are derived
from naturally occurring feedstocks, such as wood, tall oil
rosin and terpenes. Synthetic resin materials used in these
adhesives include vinyl resins such as polyethylene or
25 polypropylene; a variety of polyester resins; polycarbonate
materials; block copolymers such as styrene isoprene styrene,
styrene butadiene styrene, and similar resins. Synthetic
resin technology has become very advanced. Typically, these
polymeric resins are usually made from petroleum sources,
30 have attractive fiber and structural properties, are low in
cost and are easily processed. Formulation technology for
the manufacture of a variety of blended useful products is
well advanced. Many synthetic resin materials can be
biodegradable/compostable and can be recycled. However, the
35 chemical nature of the materials used in the formulation HMA's
is such that no currently available blend of the resin or
polymer material with other components is fully subject to

degradation by microbial populations in the biodegradable/compostable context. A substantial need has arisen for adhesives and, in particular, hot melt adhesives that are biodegradable/compostable in the appropriate environment including municipal composting facilities.

One effort to manufacture partially biodegradable/compostable adhesives is disclosed in Kauffmann et al., United States Patent No. 5,169,889, which discloses a hot melt adhesive composition made by combining a linear polyester comprising 3-hydroxy butyric acid and 3-hydroxy pentanoic acid (3-hydroxy valeric acid) (PHBV). These PHBV materials known under the tradename BIOPOL[®] are sold by Zeneca. The PHBV polymers are versatile polymers that are environmentally degradable. The PHBV polymer containing adhesive compositions, disclosed in Kauffmann et al., are not fully biodegradable/compostable because of other materials in the polymer blend. Both non-biodegradable tackifiers and plasticizers are used. These adhesive formulations can still resist substantial biodegradation because of the presence of non-degradable components. Edgington, G. J., Ryan, L. L., Biodegradable Hot Melt Adhesives. Paper Presented at the INDEX 93 International Congress for the Nonwovens Industries, Geneva, Switzerland, 1993. Accordingly, a substantial need exists to develop biodegradable/compostable adhesive compositions, particularly hot melt adhesive compositions comprising a thermoplastic resin, a tackifier and a plasticizer (each fully biodegradable/compostable) that can be blended in a hot melt product to obtain adhesive, preferably pressure sensitive adhesive properties.

Brief Description of the Invention

We have found a biodegradable/compostable tackifying resin, having a molecular weight less than 30,000, preferably less than 20,000 based on 2-hydroxy propanoic acid (lactic acid) that can be combined with biodegradable/compostable polymers or resins to form fully formulated biodegradable/compostable hot melt adhesives and hot melt

pressure sensitive adhesives. We have further found classes of biodegradable/compostable thermoplastic resins having a molecular weight greater than 30,000, that can be used with the tackifier of the invention. Such resins include but are not limited to a high molecular weight polylactic acid polymer, a polyester urethane or a high molecular weight PHBV polymer. Further, we have identified compatible small molecule compostable plasticizers that can be combined with the compostable thermoplastic resins and the tackifying resins of the invention.

In the broadest aspect of the invention, we have found that the polylactic acid (PLA) material can be useful as an adhesive (used on a 100 wt-% basis) or as a resin or tackifier component in adhesive compositions and can provide a variety of useful properties. If combined with other degradable or compostable materials, the fully formulated adhesive can be biodegradable/compostable in appropriate environments.

A first aspect of the invention resides in the biodegradable/compostable tackifying resin, based on a PLA. Preferred materials have a molecular weight of less than or equal to 30,000, preferably less than 20,000 grams per mole comprising 2-hydroxy propanoic acid. Further, the tackifying resins can be modified to improve their tackifying utility in adhesive compositions. Lactic acid can act directly as a food source for microbial populations. The tackifying resins containing substantial amounts of lactic acid are directly degradable/compostable. A second aspect of the invention provides a thermoplastic resin used in the formulation of biodegradable/compostable hot melt adhesive. Such thermoplastic resins include, but are not limited to: (1) a thermoplastic polylactic acid polymer resin, (2) a resin grade or high molecular weight thermoplastic polyester such as a polyester urethane, or (3) a thermoplastic PHBV polymer with the tackifying resin of the invention. Such adhesive compositions can also be manufactured using fully biodegradable/compostable 2-hydroxy-propionic acid based

tackifiers which we have identified as fully degradable. Edgington, G. J., M. Mulligan, Compostable Hot Melt Adhesives: An Update, Paper presented at the Insight 93 International conferences, Toronto Canada 1993. The fully
5 formulated biodegradable/compostable adhesive compositions can comprise from 10-90 wt-% of the 2-hydroxy propanoic acid based tackifying resins of the invention; 10-50 % of a thermoplastic polyester urethane, a polylactic acid resin (Mn greater than 20,000 grams per mole) or a PHBV thermoplastic
10 resin containing 5-35 wt-% of the hydroxy valerate component; 0-45 wt-% of degradable compostable ester plasticizer; and 0-5 wt-% of a stabilizer or stabilizer package. The term "tackifying agent" typically refers to a relatively low molecular weight material that when added to a thermoplastic
15 resin results in a composition having substantial and measurable tack.

Detailed Description of the Invention

The tackifying resin materials of the invention can be
20 biodegradable/compostable amorphous resins made from at least 5 mole-%, preferably 10 mole-% or most preferably 50 mole-% of either a *d*-2-hydroxy propanoic acid, or a *l*-2-hydroxy propanoic acid or mixtures thereof.

Useful tackifier resins of the invention can contain as
25 little as 5 mole-% 2-hydroxy-propanoic acid in a polymer with other reactive polymer forming materials. Either the *d*-isomer or the *l*-isomer or mixtures of isomers can be used. Preferred tackifier grade materials are polymers made using 2-hydroxy propanoic acid commonly and having at least 0-100
30 mole-%, preferably 50-95 mole-%, most preferably 50-85 mole-% of *l*-2-hydroxy propanoic acid in the polyester, the balance comprising *d*-2-hydroxy propanoic acid or other polymerizable reactive monomer compounds. These materials can be made in combination with other biodegradable/compostable monomers
35 including hydroxy substituted carboxylic acid, amine substituted carboxylic acid; mono-, di- or tricarboxylic acid materials; mono- di-, tri- or other polyol materials. The

polyesters of the invention can be homopolyesters comprising repeating units derived solely from either d- or l-2-hydroxy propanoic acid monomer or mixtures thereof or a copolyester made from the 2-hydroxy propanoic acid or other monomer materials. Polymers comprising 2-hydroxy propanoic acid can be made by polymerizing the free 2-hydroxy propanoic acid monomer or by polymerizing lactide, a stable cyclic dimer comprising 2 moles of 2-hydroxy propanoic acid or by transesterification or hydrolysis of high molecular weight polylactide. In addition to the 2-hydroxy propanoic acid starting material, other comonomers can be used including lactones such as epsilon capro-lactone, beta-propio-lactone, alpha,alpha-dimethyl-beta-propio-lactone, dodecano-lactone, lactams such as capro-lactam, other hydroxy acids such as glycolic acid, 3-hydroxy butyric acid, 3-hydroxy valeric acid, amino acids such as phenylalanine, glycine and valine, etc. Additional useful monomers are disclosed in Murdock, United States Patent No. 4,800,219. The homopolyester and copolyester materials can also be made from aromatic mono-, di- or tri-carboxylic acids or from monohydroxy alcohols and polyols comprising diols and triols. The carboxylic acid materials that can be used in the invention typically contain at least 1, 2, or 3 free reactive carboxyl groups attached to a substantial hydrocarbon moiety. Examples of such acids include benzoic acid, oxalic acid, succinic acid, maleic acid, fumaric acid, citric acid, 1,6-hexanedioic acid, phthalic acid, terephthalic acid, adipic acid and others. Further low and high molecular weight monohydroxy alkanols, diols and triols can be used in manufacturing the polyesters of the invention. Such alcohols include methanol, ethanol, isopropanol, n-butanol, benzyl alcohol, such polyol compounds include ethylene glycol, propylene glycol, glycerine, polyethylene glycol (polyoxyethylene made by polymerization of ethylene oxide) compounds, polypropylene glycol (polyoxypropylene made by polymerization of propylene oxide) compounds and other well known polyol materials.

When formed, such tackifying resins may have pendant

hydroxy and carboxyl functionality that can be reacted with an isocyanate compound to form polyester urethane materials. Typically, an amount of the isocyanate compound is used such that little or no free reactive isocyanate groups are left in the urethane material. Any minimal residual of active isocyanate groups can be reacted to destroy NCO reactivity. Such NCO groups can be reacted with water or other small molecule active hydrogen containing compounds such as alcohols, thiols, small molecule carboxylic acids, etc.

The homopolyester and copolyester tackifying resin may be synthesized by polymerization directly from hydroxy acid precursors or by polymerization of cyclic monomers of the hydroxy acid or amide precursors or from the cyclic dimeric lactone of the hydroxy acid precursor. Preferably, the preferred tackifier materials are made by polymerizing the 2-hydroxy propanoic acid monomer. Tackifier materials of the invention commonly have a molecular weight of at least 500 g/mole, preferably about 2000 to 6000. The preferred tackifier has a glass transition temperature greater than about 0°C and less than 60°C, preferably between about 20 and 50°C.

As little as 5 mole-% of the 2-hydroxy-propanoic acid can in a preferred system make a noncompostable material into a biodegradable/compostable material. The random distribution of the 2-hydroxy-propanoic acid units provide degradable sites in the molecule that can be cleaved by hydrolysis or microbial populations. The materials after degradation have substantially reduced molecular weights and improved bioavailability.

The homopolyester and copolyester tackifying resins of the invention are commonly made by known commonly available general condensation polymerization procedures wherein the monomer or mixture of monomers are raised to an elevated temperature sufficient to form an ester bond and volatilize the reaction by-product which is commonly water, when the reaction is between a free hydroxyl and a free carboxyl group. If an esterified carboxyl is reacted with a free

hydroxyl group to form a ester linkage, the reaction by-product is often a lower alcohol which can be removed by the action of heat and/or vacuum using well understood esterification condensation polymerization procedures.

5 Commonly, the monomer material(s), blended in appropriate proportions with catalysts or stabilizer materials, are introduced into a heated melt reaction chamber until they reach an adequate polymerization temperature which commonly ranges from about 100°C to about 300°C, preferably about
10 150°C to about 230°C. The reactions tend to be exothermic in nature and can be driven to produce high molecular weight polyester material. A number of catalysts have been discovered for use in the manufacture of the polyester materials including anionic substituted ion exchange resins,
15 transition metal catalysts including titanium tetrabutoxide, stannic alkoxides, stannous alkoxides, stannous octoate, stannous oleate, etc. The catalysts are often used in amounts that range from about 10^{-5} to 10^{-3} moles of catalyst per mole of total monomer material.

20 The low molecular weight polyesters described above can be effective tackifiers for high molecular weight thermoplastic resin grade biodegradable/compostable polymer materials. A variety of resin grade thermoplastic resins can be tackified using the low molecular weight poly-2-hydroxy
25 propanoic acid based material.

The tackifying resin compositions of the invention can be combined with thermoplastic resins that are biodegradable or compostable to form adhesive compositions. Biodegradable or compostable resins typically contain hydrolyzable bioreactive
30 functional groups, linking substantially hydrocarbon groups, that can be attacked typically by microbial (bacterial or fungal) populations and can act as a food source from the population. Typical biodegradable reactive groups include ester groups

35 (-O-CO-), urea linkages (-NH-CO-NH), carbamate links (-O-CO-NH-), amide (-CO-NH-), etc. Such linkages can be chemically degraded or attacked by the microbial populations

substantially reducing the molecular weight of the resin to materials that can be absorbed in and metabolized by commonly available microbial populations. The biodegradable/compostable thermoplastics commonly have a
5 molecular weight of greater than about 20,000 preferably greater than 30,000 and often include regions that produces substantial crystallinity upon cooling.

We have found three broad classes of useful thermoplastic resins that can be used in adhesives of the invention. Such
10 thermoplastics include high molecular ($M_n > 20,000$, preferably $> 30,000$) weight polylactic acid resins, PHBV resins, and polyester urethane thermoplastics.

The preferred thermoplastic resin comprises high molecular weight linear polyesters of polylactic acid (2-
15 hydroxy propionic acid). The preferred linear polyesters comprise a substantial proportion greater than 75 wt-%, preferably greater than 85 wt-% of 2-hydroxy propionic acid in a polymer that has a molecular weight of greater than about 30,000 and preferably greater than about 40,000. The
20 highly preferred linear polyesters comprising lactic acid have at least 90 mole-% of the lactic acid monomer in the L-lactic acid isomer. Preferably greater than 90 wt-% of the lactic acid monomer is in the L-isomer. Such thermoplastics can be made as described above using conditions that promote
25 formation of high molecular weight materials.

A preferred class of thermoplastic resins useful in the adhesive compositions of the invention include polyester urethane compositions. Such materials are typically made by reacting a polyisocyanate compound (typically an isocyanate
30 compound having two or three isocyanato groups on an aromatic or aliphatic nucleus) with a polyester material. Preferred polyester materials are made by reacting a hydroxy compound having two or more hydroxy groups with an acid compound having two or more carboxyl groups to form the polyester
35 backbone. Preferred hydroxy compounds that can be used in manufacturing the polyester urethane compounds of the invention include ethylene glycol, propylene glycol, 1,4-

butene glycol, polymers made from ethylene oxide, propylene oxide, butylene oxide having two or more free hydroxyl groups and other similar diol, triol, polyol compounds. Useful acids that can be used in making the polyester urethanes of the invention include di- and tri-carboxylic acid substituted compounds. Such acids can include oxalic acid, malic acid, maleic acid, phthalic acid, terephthalic acid, pyromellitic acid and others. The polyester materials can also be made of hydroxy-carboxylic acid containing compounds. Such compounds include hydroxy acids such as lactic acid, hydroxybutyric acid, etc. and polymer materials such as polycaprolactone diols, polyethylene glycols, etc. The hydroxy compound and the acid compound is typically reacted under condensation reaction conditions with the removal of water to form ester bonds resulting in the formation of the thermoplastic polyester resin material.

Another preferred thermoplastic resin material for use in the hot melt adhesives of the invention comprises a linear polyester of 3-hydroxy butyric acid (HB) and 3-hydroxy valeric acid (HV). Such a polyester is produced by the fermentation of sugars by the bacteria *alcaligenes eutrophus*. Such materials are available from Zeneca known as BIOPOL[®] polymers, and typically contain about 5-35 wt-% of the hydroxy valerate component, the balance being hydroxy butyrate.

The hot melt adhesive compositions of the invention can contain a plasticizer compound. Plasticizers can improve the melt properties of the adhesives, can impart pressure sensitive properties, can extend the adhesive reducing cost and can increase the flexibility and melt properties of the hot melt adhesive. The preferred plasticizers for use with the hot melt adhesives of the invention are biodegradable/compostable plasticizers. Such plasticizers typically comprise naturally recurring oils or synthetic materials manufactured containing ester or urea carbamyl or amido groups as discussed above. However, plasticizer materials are different than the thermoplastic resins

discussed above in terms of molecular weight. Plasticizer compounds are typically liquid or low melting small molecule solid materials having a molecular weight less than about 5000, preferably less than 1000, that can provide plasticizer properties to the compositions of the invention. Preferred classes of plasticizer materials for use in the invention comprise natural fats and oils compatible with the thermoplastic resins disclosed herein. A further preferred class of plasticizers for use in the adhesives of the invention include ester plasticizers typically made by reacting aromatic or aliphatic small molecule mono-, di- or triols with an aromatic or aliphatic acid compositions. Specific examples of preferred plasticizers include castor oil, TegMer 809-PEG 400 di-2-ethylhexoate ester, Plasthall DBS-dibutyl sebacate, Plasthall DIBA diisobutyl sebacate, Sanitizer 160, a butyl benzyl phthalate, polycaprolactone diols having a molecular weight of about 500 g/mole, a melting point less than about 25°C, ethylene glycol dibenzoate, propylene glycol dibenzoate, diethylene glycol dibenzoate, dipropylene glycol dibenzoate, pentaerythritol tetrabenzoate, sucrose benzoate.

Castor oil comprising an oil obtained by cold pressing seeds of *Ricinus Communis* L comprising triglycerides of fatty acids comprising 87 wt-% ricinoleic acid, 7 wt-% oleic acid, 3% linoleic acid, 3% palmitic acid, 1% stearic acid, and trace amounts of other fatty acids can be used. Other natural oils of vegetable sources which have an I_2 value of about 100 or less can be useful for the hot melt adhesives of the invention.

Apart from useful tackifiers and plasticizers used to obtain the final adhesive properties, other suitable additives such as dyes, pigments, fillers, antioxidants, stabilizers, etc. may be employed in the polyester materials in conventional amounts. Such additives may be added directly to a reaction mixture or may be post-added to the final polymer before or after final formulation is complete.

Formulations

The hot melt adhesive compositions of the invention can comprise formulations set forth in Table I found below.

TABLE IFormulations A

	<u>Ingredient</u>	<u>Wt-%</u>		
		<u>Useful</u>	<u>Preferred</u>	<u>Most Preferred</u>
10	Resin Grade Thermoplastic PLA ¹ (M _n >30,000 gm/mole, high - mw)	0-100	10-50	15-35
15	PLA Tackifier	20-100	20-90	35-75
	Plasticizer	0- 45	15-50	15-40
20	Stabilizer	0- 5	0- 3	0.01- 2

Formulations B

	<u>Ingredient</u>	<u>Wt-%</u>		
25	Resin Grade Thermoplastic Polyester Urethane	0- 50	10-50	15-40
	PLA Tackifier	20-100	20-90	35-75
30	Plasticizer	0- 45	15-40	15-35
	Stabilizer	0- 5	0- 3	0.01- 2

Formulations C

	<u>Ingredient</u>	<u>Wt-%</u>		
40	Resin Grade Thermoplastic PHBV	0- 50	10-50	15-40
	PLA Tackifier	20-100	20-90	40-75
45	Plasticizer	0- 45	15-40	15-35
	Stabilizer	0- 5	0- 3	0.01- 2

50

¹ Polyester comprising 2-hydroxy propionic acid.

Examples and Data

The following examples serve to further illustrate the hot melt adhesives of the invention. The adhesives were tested and test data relating to adhesion and thermal
5 stability follows the operating examples. Further, the examples and data contain a best mode.

Examples

Lactic Acid Based Tackifying Resin

10

Example 1A

From Lactic Acid

To a nitrogen purged reaction vessel was added 500 g 85% lactic acid and 17.00 g benzyl alcohol. The mixture was slowly heated to 200°C while removing water by distillation.
15 The mixture was heated at 200°C for 4 hours, reduced to 165°C and vacuum applied for 3 hours. 26.45 g Desmodur H was then added dropwise at 120°C and allowed to react an additional 1 hour to yield a yellow brittle solid.

Example 1B

20 From Lactic Acid

To a reaction vessel purged with dry N₂ for 1 hour at 120°C was added 250 g d,l-lactide, 4.5 g 1,4-butane diol and 2 drops Metacure T-9 catalyst under positive nitrogen pressure. The mixture was purged with dry N₂ for an
25 additional 1 hour and the temperature then raised to 150°C for 18 hours to yield a light yellow brittle solid.

Example 1C

From Polylactide

To a nitrogen purged reaction vessel was added 500 g d,l-poly
30 polylactide (Mn about 90,000 g/mole), 24.16 g benzyl alcohol and 1.0 g Fascat 9100. The temperature was slowly raised to 190°C for 6 hours to yield a yellow brittle solid.

Experimental compostable HMA's have been formulated from about 20-25 wt-% of a compostable thermoplastic (A), with 50-
35 60 wt-% of an experimental compostable poly(lactic acid), (PLA) based tackifying resin (B), and 20-25 wt-% of two commercially available compostable plasticizers (C, Benzoflex

9-88, D Sanitizer 160-butyl benzyl phthalate.

The experimental tackifying resin (B) is representative of a variety of PLA-based tackifying resins developed in our laboratories. This resin possesses a 60°C ring and ball softening point and was shown to be compostable. This strongly contrasts with previous testing which determined that three polar commercial tackifying resins based on natural products were not compostable. The two commercial plasticizers C and D were found to be compostable.

Two HMA formulations (I and II) were bonded to a compostable poly(lactic acid) spun bond non-woven fabric at 15 psi and 60°C for 1 second. After conditioning at ambient temperature for 24 hours, adhesive performance was measured by an in-house T-Peel method. Viscosity measurements were determined at 150°C after 1 and 4 hours using a Brookfield viscometer (spindle 27 at 10 rpm). Formulation II was run at 135°C after 1, 4 and 15 hours using a spindle # 27 at 20 rpm.

14

Table 1

<u>HMA Formulation I*</u>		<u>Wt-%</u>
5	Resin grade polylactide (99% l-isomer) polymer	20.0
	Lactic acid based tackifying resin	54.0
10	Sanitizer 160	24.5
	Irganox 1010 (stabilizer)	1.0
15		
	<u>Substrate</u>	<u>T-Peel Strength</u> <u>(Avg. g)</u>
		<u>Failure Mode</u>
20	Poly(lactic acid)	166 g C.F.
	Poly(vinyl alcohol)	= 0 g A.F.
	Starch-polycaprolactone	31 g A.F.
25	Polycaprolactone	140 g C.F.
	<hr/>	
30	*Kraft to Kraft 100 g peel failure temperature (H.B. Fuller test method TMHM-023) for HMA (III)	86°F
	Kraft to Kraft 500 g shear failure temperature (H.F. Fuller test method TMHM-023) for HMA (III)	90°F
	<hr/>	
35	Viscosity 5750 at 1 hour 4810 at 4 hours	4000 at 15 hours

15

Table 2

	<u>HMA Formulation II</u>	<u>Wt-%</u>	
5	PHBV (22% valerate)	25	
	PLA based tackifier (benzyl alcohol end capped 50/50 d, 1-poly(lactic acid) with $M_n = 3,300$ g/mole.	55	
	Benzoflex 9-88 SG	20	
15			
	<u>Substrate*</u>	<u>T-Peel Strength (Avg. g)*</u>	<u>Failure Mode**</u>
	Poly(lactic acid)	479	S.F.
20	Poly(vinyl alcohol)	401	S.F.
	Starch-Polycaprolactone	= 0	A.F.
	Polycaprolactone	= 0	A.F.
25	Viscosity (at 150°C) 15,000 cps at 1 hour	8,500 cps at 4 hours	

* Various compostable films bonded to a compostable PLA non-woven.

30 ** A.F. = Adhesive Failure, C.F. = Cohesive Failure,
S.F. = Substrate Failure

35

16

Table 3

<u>HMA Formulation III</u>		<u>Wt-%</u>
5	PHBV (22% valerate)	23
10	PLA based tackifier (benzyl alcohol end capped 50/50 d, 1-poly(lactic acid) with $M_n = 3,300$ g/mole.	57
	Sanitizer 160	20
15	<u>Substrate*</u>	<u>T-Peel Strength (Avg. g)</u>
	Poly(lactic acid)	338
20	Poly(vinyl alcohol)	287
	Starch-Polycaprolactone	206
25	Polycaprolactone	= 0
	Viscosity (at 150°C) 11,500 cps at 1 hour	6,000 cps at 4 hours
30	* Various compostable films bonded to a compostable PLA non-woven.	
	** A.F. = Adhesive Failure, C.F. = Cohesive Failure, S.F. = Substrate Failure	

35

40 In all cases, substrate failure indicates failure of the non-woven. T-Peel values of samples that showed adhesive failure were reported to show that the biodegradable substrates possessed adequate strength. For comparison, a standard commercial HMA applied to polyethylene and bonded to a polyolefin spun bond non-woven fabric (1.2 mg/inch) showed T-

45 peels values of about 150 g. Therefore, these compostable HMAs possess adhesive properties that fall within a usable range.

The compositions used in the hot melt adhesive compositions formulated below when tested for

50 biodegradability and compostability were tested under the

ASTM D5338-92 Standard Test Method for Determining Aerobic Biodegradation of Plastic Materials Under Controlled Composting Conditions. The compositions below were tested for peel strength to determine bonding strength of an adhesive when subjected to a dynamic peel force. In the test, fine lines were applied at 2-3 mg/linear inch directly to substrates measuring 1 x 6 inches. The samples were pressed at 15 psi and 140°F for 1 second. T peels were run on 7 to 8 samples at room temperature using a cross set speed of 12 inches per minute and a 25 second dwell time. The cross head motion is initiated and continued for 10 seconds recording the peak and average peel values. Typically, the results are reported including average maximum force to rupture (in grams), failure mode (adhesive failure, substrate failure or cohesive failure).

In the following tables the formulations were blended by combining the materials in a steel container with a high speed mixer. While the order of addition is not critical, the materials were made by first melting the tackifier and then adding the resin grade thermoplastic followed by the plasticizer.

Kraft to Kraft heat resistance testing was performed by laminating 18 pound Kraft paper to form a one inch by one inch bond area with an approximate bond thickness of 5 mils. Weights were attached in the peel and shear modes and the samples placed in an oven. The temperature was raised at 25°C and the temperature at which the bond delaminated was recorded.

The above discussion, examples and embodiments illustrate our current understanding of the invention. However, one skilled in the art will appreciate that various changes may be made without departing from the spirit and scope of the invention. Thus, the invention resides wholly in the claims hereafter appended.

WE CLAIM:

1. A tackifying resin composition comprising a polyester material comprising greater than 5 mole-% of lactic acid having a molecular weight (Mn) less than about 30,000 grams per mole and T_g less than 110°C.
5
2. The composition of claim 1 wherein the concentration of the lactic acid is about 10 mole-%.
3. The composition of claim 1 wherein the concentration of the lactic acid is about 50 mole-%.
- 10 4. The composition of claim 1 wherein the T_g is less than about 90°C.
5. The composition of claim 1 wherein the T_g is less than about 60°C.
6. The composition of claim 1 wherein the lactic acid
15 component of the tackifying resin comprises 40-100 mole-% of l-lactic acid and 0-60 mole-% of d-lactic acid and a molecular weight (Mn) less than 20,000 g/mole.
7. The composition of claim 1 wherein the tackifying resin comprises 50-95 mole-% of l-lactic acid and 1-50 wt-%
20 of d-lactic acid and a molecular weight (Mn) less than 20,000 g/mole.
8. The composition of claim 1 wherein the molecular weight (Mn) of the tackifying resin is about 2000-6000 grams per mole.
- 25 9. The composition of claim 3 wherein the tackifying resin has a T_g of about 0 to 50°C.
10. A biodegradable/compostable hot melt adhesive composition comprising:
 - (a) about 0-50 wt-% of a biodegradable/compostable
30 thermoplastic resin; and
 - (b) about 20-100 wt-% of a biodegradable tackifying resin composition comprising a polylactic acid composition having a molecular weight (Mn) of less than about 20,000 grams per mole, a T_g of less than about 60°C.
- 35 11. The composition of claim 10 wherein the adhesive additionally comprises about 1-45 wt-% of a biodegradable/compostable plasticizer and about 20-90 wt-% of

the tackifying resin.

12. The composition of claim 10 wherein there is about 10-50 wt-% of a biodegradable/compostable thermoplastic resin that comprises a polymeric material having a molecular weight
5 (Mn) of greater than 30,000 grams per mole.

13. The composition of claim 10 wherein the tackifying resin comprises a polymer comprising 40-100 mole-% of L-lactic acid and 0-60 mole-% of D-lactic acid.

14. The composition of claim 10 wherein the tackifying
10 resin comprises a polymer comprising 50-95 mole-% of L-lactic acid and 1-50 mole-% of D-lactic acid.

15. The composition of claim 11 wherein the plasticizer comprises an ester composition derived from an aromatic or aliphatic mono-, di- or tri-carboxylic acid.

16. The composition of claim 11 wherein the plasticizer
15 comprises a fatty oil.

17. A biodegradable/compostable hot melt adhesive composition comprising:

(a) about 10-50 wt-% of a resin grade thermoplastic
20 polylactic acid resin having a molecular weight (Mn) greater than about 30,000 grams per mole; and

(b) about 20-100 wt-% of a tackifying resin composition comprising a polymer of lactic acid having a molecular weight (Mn) less than about 20,000 grams per
25 mole and a T_g of about -20 to 60°C.

18. The composition of claim 17 wherein the thermoplastic resin comprises greater than 90 mole% lactic acid.

19. The composition of claim 17 wherein the tackifying resin is present at a concentration of about 95 wt% and has a
30 T_g of about 0 to 50°C.

20. The composition of claim 17 wherein the T_g of the thermoplastic resin is about 50 to 65°C, the T_g of the tackifying resin is about -10° to 50°C and the T_g of the adhesive is
35 about -25° to 25°C.

21. The composition of claim 17 wherein the adhesive

additionally comprises about 1-50 wt-% of a biodegradable/compostable plasticizer.

22. The composition of claim 17 wherein the biodegradable/compostable thermoplastic resin comprises a
5 polymeric material having a molecular weight (Mn) of greater than 40,000 grams per mole.

23. The composition of claim 17 wherein the tackifying resin comprises a polymer comprising 50-100 mole-% of l-lactic acid and 0-50 mole-% of d-lactic acid.

10 24. The composition of claim 17 wherein the tackifying resin comprises a polymer comprising 50-95 mole-% of l-lactic acid and 1-50 mole-% of d-lactic acid.

25. The composition of claim 21 wherein the plasticizer comprises an ester composition derived from an aromatic or an
15 aliphatic mono-, di- or tri-carboxylic acid.

26. A biodegradable/compostable hot melt adhesive composition comprising:

(a) about 10-50 wt-% of a thermoplastic polyester urethane resin having a molecular weight (Mn) greater
20 than 30,000; and

(b) about 20-90 wt-% of a tackifying resin composition comprising a polymer of lactic acid having a molecular weight (Mn) less than about 30,000 grams per mole and a T_g of less than 110°C.

25 27. The composition of claim 26 wherein the tackifying resin has a T_g of about 10 to 80°C.

28. The composition of claim 26 which additionally comprises about 1-50 wt-% of a compatible biodegradable/compostable plasticizer.

30 29. The composition of claim 26 wherein the adhesive additionally comprises about 1-45 wt-% of a biodegradable/compostable plasticizer.

30. The composition of claim 26 wherein the biodegradable/compostable thermoplastic resin comprises a
35 polymeric material having a molecular weight (Mn) of greater than 40,000 grams per mole.

31. The composition of claim 26 wherein the tackifying

resin comprises a polymer comprising 40-100 mole-% of *l*-lactic acid and 0-60 mole-% of *d*-lactic acid having a molecular weight (Mn) less than 20,000.

32. The composition of claim 26 wherein the tackifying
5 resin comprises a polymer comprising 50-95 mole-% of *l*-lactic acid and 1-50 mole-% of *d*-lactic acid having a molecular weight (Mn) less than 20,000.

33. The composition of claim 28 wherein the plasticizer
10 comprises an ester composition derived from an aliphatic or aromatic mono-, di- or tri-carboxylic acid.

34. A biodegradable/compostable hot melt adhesive composition comprising:

(a) a linear thermoplastic polyester resin comprising 1-95 wt-% of a hydroxy butyric acid
15 composition and about 5-35 wt-% of a hydroxy valeric acid composition; and

(b) about 20-90 wt-% of a biodegradable tackifying resin composition comprising a polylactic acid polymeric composition having a molecular weight (Mn) of less than
20 about 30,000 grams per mole, a T_g of less than about 110°C.

35. The composition of claim 34 wherein the tackifying resin has a T_g of about 10 to 80°C.

36. The composition of claim 34 wherein the adhesive
25 additionally comprises about 1-50 wt-% of a biodegradable/compostable plasticizer.

37. The composition of claim 34 wherein the biodegradable/compostable thermoplastic resin comprises a polymeric material having a molecular weight (Mn) of greater
30 than 40,000 grams per mole.

38. The composition of claim 34 wherein the tackifying resin comprises a polymer comprising 40-100 mole-% of *l*-lactic acid and 0-60 mole-% of *d*-lactic acid.

39. The composition of claim 34 wherein the tackifying
35 resin comprises a polymer comprising 50-95 mole-% of *l*-lactic acid and 1-50 mole-% of *d*-lactic acid.

40. The composition of claim 34 wherein the plasticizer

comprises an ester composition derived from an aromatic or aromatic mono-, di- or tri-carboxylic acid.

41. A method of joining at least two substrates which comprises applying an effective adhesive amount of an
5 adhesive comprising a linear polyester comprising 2-hydroxy-propionic acid to an interface between the substrates.

42. The method of claim 41 wherein the adhesive comprises the adhesive of claim 17.

43. The method of claim 41 wherein the substrates are
10 biodegradable/compostable.

INTERNATIONAL SEARCH REPORT

International Application No
PCT/US 94/09666

A. CLASSIFICATION OF SUBJECT MATTER

C 09 J 167/04, C 08 G 63/08, C 08 L 67/04

According to International Patent Classification (IPC) or to both national classification and IPC⁶

B. FIELDS SEARCHED

Minimum documentation searched (classification system followed by classification symbols)

C 09 J, C 08 G, C 08 L

Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched

Electronic data base consulted during the international search (name of data base and, where practical, search terms used)

C. DOCUMENTS CONSIDERED TO BE RELEVANT

Category *	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
X	DERWENT ACCESSION no. 83-708300, Questel Telesystems (WPIL), DERWENT PUBLICATIONS LTD., London; & JP, A, 58 093 767, abstract.	1-3
X, P	DERWENT ACCESSION no. 94-032 009, Questel Telesystems (WPIL), DERWENT PUBLICATIONS LTD., London; & JP, A, 05 339 557, abstract.	1, 10
X	US, A, 5 252 646 (IOVINE) 12 October 1993 (12.10.93),	1, 10

☒ Further documents are listed in the continuation of box C.☐ Patent family members are listed in annex.

* Special categories of cited documents :

- "A" document defining the general state of the art which is not considered to be of particular relevance
- "E" earlier document but published on or after the international filing date
- "L" document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)
- "O" document referring to an oral disclosure, use, exhibition or other means
- "P" document published prior to the international filing date but later than the priority date claimed

"T" later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention

"X" document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone

"Y" document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art.

"&" document member of the same patent family

Date of the actual completion of the international search
16 December 1994

Date of mailing of the international search report

17. 01. 95

Name and mailing address of the ISA

European Patent Office, P.B. 5818 Patentlaan 2
NL - 2280 HV Rijswijk
Tel. (+ 31-70) 340-2040, Tx. 31 651.spo nl,
Fax: (+ 31-70) 340-3016

Authorized officer

PAMMINGER e.h.

INTERNATIONAL SEARCH REPORT

International Application No
PCT/US 94/09666

C.(Continuation) DOCUMENTS CONSIDERED TO BE RELEVANT

Category *	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
X	claims; example. -- EP, A, 0 468 199 (BOEHRINGER INGELHEIM KG) 29 January 1992 (29.01.92), claims; page 2, lines 45-48. -----	1-8

Form: PCT/ISA/210 (continuation of second sheet) (July 1992) *

ANHANG

zum internationalen Recherchen-
bericht über die internationale
Patentanmeldung Nr.

ANNEX

to the International Search
Report to the International Patent
Application No.

ANNEXE

au rapport de recherche inter-
national relatif à la demande de brevet
international n°

PCT/US 94/09666 SAE 96246

In diesem Anhang sind die Mitglieder
der Patentfamilien der im obenge-
nannten internationalen Recherchenbericht
angeführten Patentdokumente angegeben.
Diese Angaben dienen nur zur Unter-
richtung und erfolgen ohne Gewähr.

This Annex lists the patent family
members relating to the patent documents
cited in the above-mentioned inter-
national search report. The Office is
in no way liable for these particulars
which are given merely for the purpose
of information.

La présente annexe indique les
membres de la famille de brevets
relatifs aux documents de brevets cités
dans le rapport de recherche inter-
national visé ci-dessus. Les renseigne-
ments fournis sont donnés à titre indica-
tif et n'engagent pas la responsabilité
de l'Office.

Im Recherchenbericht angeführtes Patentdokument Patent document cited in search report Document de brevet cité dans le rapport de recherche		Datum der Veröffentlichung Publication date Date de publication	Mitglied(er) der Patentfamilie Patent family member(s) Membre(s) de la famille de brevets	Datum der Veröffentlichung Publication date Date de publication
US A 5252646		12-10-93	AU A1 51332/93	24-05-94
			CA AA 2126849	11-05-94
			EP A1 618948	12-10-94
			WD A1 9410257	11-05-94
			US A 5312850	17-05-94
EP A1 468199		29-01-92	DE A1 4028764	12-03-92
			JP A2 4226125	14-08-92
			US A 5302693	12-04-94
			EP A1 463194	02-01-92

THIS PAGE BLANK (USPTO)